

# UHMW-PE

(ultra high molecular weight polyethylene)

## POLYSTONE® M



Polyethylene is a low cost, chemically resistant plastic material that can be used for a wide variety of applications. The versatility of polyethylene has made it one of the world's most popular plastics. Polyethylene is available in a number of grades according to its molecular weight.

UHMW-PE (ultra high molecular weight polyethylene) is an extremely tough and abrasion resistant thermoplastic that is used for applications that require durability and/or abrasive wear resistance.

UHMW sheet is often used for lining chutes and hoppers in order to protect metal surfaces and promote the flow of solid materials such as sand, wood chips, or coal. UHMW is also used for packaging, conveyor, and food processing machinery parts including star wheels, idler sprockets, and under-chain wear strips.



### KEY CHARACTERISTICS:

- Extremely tough and durable
- Low friction
- Excellent abrasion resistance
- Good chemical resistance
- Low water absorption
- Easy to fabricate
- Reprocessed grades available
- Enhanced bearing and wear grades available
- FDA compliant grades available

### APPLICATIONS:

- Chute liners and hopper liners
- Wear strips
- Star wheels
- Idler sprockets
- Packaging machinery components
- Food processing machinery components

### POLYETHYLENE TYPICAL PROPERTIES:

|   | UNITS                     | ASTM TEST | LDPE     | HDPE    | UHMW-PE |
|---|---------------------------|-----------|----------|---------|---------|
| Tensile strength                              | psi                       | D-638     | 1,400    | 4,000   | 3,100   |
| Flexural modulus                              | psi                       | D-790     | 30,000   | 200,000 | 110,000 |
| Izod impact (notched)                         | ft-lbs/in of notch        | D-256     | no break | 1.3     | 18.0*   |
| Heat deflection temperature @66 psi           | °F                        | D-648     | 122      | 172     | -       |
| Maximum continuous service temperature in air | °F                        |           | -        | -       | 180     |
| Water absorption (immersion 24 hours)         | %                         | D-570     | 0.10     | 0.10    | slight  |
| Coefficient of linear thermal expansion       | in/in/°Fx10 <sup>-5</sup> | D-696     | -        | 7.0     | 11.1    |

**UHMW Standard Sizes: SHEET: 48"x96" (0.062"-4.0" thick), 48"x120" (0.062"-7.0" thick), 48"x144" (0.375"-4.0" thick), 60"x96" (0.375"-4.0" thick), 60"x120" (0.375"-4.0" thick) POLYSTONE® MEGASHEET: 96"x240" (0.375"-4.0" thick) ROD: diameter 0.25"-10.00" TUBE: diameter 2.0"-9.398"**

Length, width, thickness, and diameter tolerances vary by size and by manufacturer • Custom sizes and colors available upon request • Many of our materials are available as films with thicknesses of 0.029" or less. Values may vary according to brand name. Please ask your Curbell Plastics representative for more specific information about an individual brand. \*Double-15° notch

**Curbell Plastics has been supplying plastic sheet, rod, tube, films, adhesives, sealants, and prototyping materials for over 65 years**



NATIONWIDE  
**1.888.CURBELL**  
[www.curbellplastics.com](http://www.curbellplastics.com)

©2008 Curbell Plastics, Inc. All other trademarks and service marks are property of the respective manufacturers. All statements, technical information and recommendations contained in this publication are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that Curbell, Inc. cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of specific products in any given application. UHMWDataSheet 0308